

VOYAGER MARINESAFE



MARINESAFE







2.0mm

 $2m \times 20m = 40m^2$

2250./



GENERAL PERFORMANCE

EN 13845









MARITIME USAGE

US Coast Guard Marine Equipment Directive 96/98/EC SOLAS 74 REACTION TO FIRE

IMO MSC 61 (67) Annex 1 Part 2 and 5 - Pass





SLIP RESISTANCE

Sustainable wet slip resistance*

EN 13845 ESf

RRL Pendulum Test ≥36 (wet test - 4S Rubber/Slider 96)

Surface roughness Rz ≥ 20µm

The slip resistance of Voyager MarineSafe is assured throughout the guaranteed life of the product, with strict adherence to Health and Safety Executive Guidelines.



ABRASION RESISTANCE

EN 13845 50,000 cycles



LIGHT FASTNESS

ISO 105-B02 Method 3 ≥6

RESISTANCE TO CHEMICALS

Good resistance to dilute acids and alkalis



DIMENSIONAL STABILITY

EN 434 ≤ 0.4% max.

FLEXIBILTY

Pass 20mm mandrel



INDENTATION - RESIDUAL

EN 433 ≤ 0.1mm



ENVIRONMENTALLY PREFERABLE FLOORING

Voyager MarineSafe is 100% recyclable and contains 25% recycled material.



APPLICATIONS

Voyager MarineSafe is ideal for use in areas on marine vessels which are normally dry but where occasional water spillage can occur, making slip resistance an important consideration. Typical areas include stairway enclosures, control stations, staff quarters, en-suites, back of house corridors, circulation areas, general service spaces, washrooms, WCs, bar serveries, food preparation areas, kitchens and canteens.

Voyager MarineSafe should not have a polish applied as it will impair the slip resistance of the floor.



For information regarding handling and installation, adhesives, maintenance, applications and chemical resistance, consult Polyflor Voyager.

The data presented is correct at the time of printing.

*For clarification regarding slip resistance, consult Polyflor Voyager.





POLYFLOR LTD. - TRANSPORT FLOORING DIVISION

PO BOX 3 RADCLIFFE NEW ROAD WHITEFIELD MANCHESTER M45 7NR UK TEL: +44 (0)161 767 1111 UK FAX: +44 (0)161 767 2515

E-MAIL: TRANSPORT@POLYFLOR.COM
WWW.VOYAGER.POLYFLOR.COM





